

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
12 September 2002 (12.09.2002)

PCT

(10) International Publication Number
WO 02/070248 A1

- (51) International Patent Classification⁷: **B32B 13/00**, E04C 1/40, 2/24, B28B 11/04 (74) Agent: **BALDWIN SHELSTON WATERS**; 60 Margaret Street, Sydney, NSW 2000 (AU).
- (21) International Application Number: PCT/AU02/00242 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 4 March 2002 (04.03.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
PR 3474 2 March 2001 (02.03.2001) AU
PR 3475 2 March 2001 (02.03.2001) AU
PR 3476 2 March 2001 (02.03.2001) AU
PR 3477 2 March 2001 (02.03.2001) AU
PR 3478 2 March 2001 (02.03.2001) AU
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): **JAMES HARDIE RESEARCH PTY LIMITED** [AU/AU]; Level 1, Research & Product Development Building, 10 Colquhoun Street, Rosehill, NSW 2142 (AU).
- Declaration under Rule 4.17:
of inventorship (Rule 4.17(iv)) for US only
- Published:
— with international search report
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **NAJI, Basil** [AU/AU]; 7A Marcia Street, Toongabbie, NSW 2146 (AU). **O'CHEE, Milton** [AU/AU]; 122 Chatham Road, Denistone, NSW 2144 (AU).
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COATINGS FOR BUILDING PRODUCTS

(57) Abstract: A method for coating a building product in which a coating formulation is provided which includes an hydraulic binder and a quantity of dewatering agent. A slurry is produced from said formulation and applied to the product to be coated. The resultant coating is then dewatered through said product. Dewatering can be accomplished with or without vacuum assistance. The method is suitable for producing a composite product which comprises a base structural layer with the coating thereon.

WO 02/070248 A1

- 1 -

TITLE: COATINGS FOR BUILDING PRODUCTS

Technical Field

This application claims priority from the following Australian provisional patent applications, the full contents of which are hereby incorporated by cross-reference.

5	Application No	Title	Date Filed
	PR3474	A Composite Product	2 March 2001
	PR3475	Spattering Apparatus	2 March 2001
	PR3476	Additive for a Dewaterable Slurry	2 March 2001
	PR3477	A Method and Apparatus for Forming a	2 March 2001
10		Laminated Sheet Material by Spattering	
	PR3478	Coatings for Building Products	2 March 2001

The present invention relates to coatings and in particular coatings for building products and laminated building products.

Background Art

15 Any discussion of the prior art throughout the specification should in no way be considered as an admission that such prior art is widely known or forms part of common general knowledge in the field.

There are a huge variety of mechanisms for applying coatings to building products such as building boards.

20 The coatings can be divided into two main groups namely finishing coatings, which are intended primarily for aesthetic purposes, and functional coatings which provide some additional structural or other property/attribute to the resultant product.

The application technique depends to a large extent on the properties of the coating composition and base layer or product to be coated. Manual application and
 25 spraying etc are most popular but they restrict the types of coating to be applied and indeed the building product to be coated. For example, when using a spray technique, one must ensure the coating composition is of sufficient flowability to pass through the spray nozzle but at the same time, the base material to be coated must be sufficiently rigid to withstand the impact of the spray coating.

30 For certain building products, such as internal wall systems, a smooth surface finish is vital. Gypsum or plaster board is used almost exclusively as an internal wall board due to its excellent surface finish.

- 2 -

The use of fibre reinforced cement building board for instance as an internal wall board has significant advantages including cost and structural integrity as compared with gypsum board. However, some techniques for production of fibre reinforced cement sheets do not provide a gypsum like surface finish. In response to public demand, builders require an internal wall board with a near perfect surface finish. Even minute irregularities which arise from production of fibre reinforced cement sheets can be sufficient to reject the product. Sanding the surface of the FRC sheet has been used to improve its surface finish but in some instances such sanding can 'feather' or leave exposed the reinforcing fibres thereby exacerbating the problem.

It is an object of the present invention to overcome or ameliorate at least one of the disadvantages of the prior art, or to provide a useful alternative.

Disclosure of the Invention

In a first aspect, the present invention provides a method for coating a building product comprising providing a coating formulation including an hydraulic binder and a quantity of dewatering agent, producing a slurry of said formulation, applying said slurry to the product to be coated and dewatering said slurry through said product.

In a second aspect, the present invention provides a formulation for use in coating a building product comprising an hydraulic binder and a quantity of dewatering agent sufficient to permit dewatering of a slurry produced from said formulation through the building product.

In a third aspect, the present invention provides a dewaterable slurry for coating a building product, said slurry comprising water, an hydraulic binder and a quantity of dewatering agent sufficient to permit dewatering of said slurry through said building product.

In a fourth aspect, the present invention provides a composite product comprising a base structural layer with a coating thereon, the coating including an hydraulic binder and a quantity of dewatering agent sufficient such that the coating may be dewatered through the base layer.

In a fifth aspect, the present invention provides a method of improving an hydraulic binder based coating formulation for coating a building product comprising adding to said binder a quantity of dewatering agent such that after application of a

- 3 -

slurry of said formulation to said building product, said slurry can be dewatered through the building product.

In a sixth aspect, the present invention provides a dewatering aid for dewatering a cementitious slurry coating on a product, said dewatering aid comprising a quantity
5 of particulate material sufficient to permit dewatering of the slurry through the product to be coated.

Unless the context clearly requires otherwise, throughout the description and the claims, the words 'comprise', 'comprising', and the like are to be construed in an inclusive sense as opposed to an exclusive or exhaustive sense; that is to say, in the
10 sense of "including, but not limited to".

The dewatering agent serves to maintain sufficient porosity in the slurry and product to be coated to permit dewatering of the slurry through the product to be coated. Preferably, the dewatering agent is a particulate material such as fly ash, alumina trihydrate, silica flour, cenospheres (ceramic hollow spheres) or similar.

15 Fly ash is particularly preferred as it permits dewatering of the slurry within a few minutes. Other particulate dewatering agents such as alumina trihydrate or silica flour may also be used, however, they increase the time required for dewatering of the slurry through the product to be coated.

In a preferred embodiment, the slurry applied to the product to be coated has a
20 high water content. Preferably, the water content can be up to 50%. This is in contrast to previous cementitious formulations which generally have a higher solids content.

By combining the various components of the coating formulation described above, a dewaterable slurry is obtained which can be applied to the building product,
25 dewatered through the building product and thereby provide a uniform coating over the building product.

Normally, after application of the coating, the resultant product would be normally cured, steam cured or hydrothermally cured, ie autoclaved, and if required, sanded to a smooth flat finish.

30 The building product to which the coating can be applied is virtually limitless provided the slurry can be dewatered through the building product. Cementitious and

- 4 -

gypsum building boards are typical examples of suitable building products on which the coating can be applied.

The resultant coating, which may optionally contain fibres, results in a decorative finishing layer which is sandable, smooth, flat, low permeable, crack free
5 and/or flexible, ready to be finished, for example by painting.

The thickness of such a coating layer prior to sanding would range from around 0.1 to 10 mm, preferably 0.5 to 5 mm and most preferably 1 to 3 mm.

After sanding, the finish layer may have a depth of around 0.05 to 5 mm, preferably 0.1 to 2 mm and most preferably 0.5 to 1 mm. The thus produced coated
10 product is comparable in its workability to monolithic (single layer) composites. It can be flexed, cut, drilled and fixed by nails etc to a frame without surface cracking or chipping.

The applicant's have found an extremely good interlaminar bond and compatibility between the dewatered slurry layer and base layer resulting in excellent
15 composite action, compatibility and resistance to delamination.

The term 'hydraulic binder' as used throughout the specification refers to a pulverised material in the solid, dry state which, when mixed with water, yields plastic mixtures that are able to set and harden, for example a cement. Included within the definition are white, grey or pigmented cements and hydraulic limes.

20 The term 'cement' includes hydraulic and alite cements such as portland cement, blended cements such as portland cement blended with fly ash, blast-furnace slag, pozzalans and the like and mixtures thereof, masonry cement, oil well cement, natural cement, alumina cement, expansive cements and the like, or mixtures thereof.

The quantity of binder in the formulation is preferably between 10 to 50 wt%
25 based on the total dry ingredients, more preferably 15 to 40 wt% and most preferably 20 to 30 wt%.

The fly ash used in the present invention provides a number of advantages including, particularly, as an aid to dewatering of the slurry as defined above.

The term 'fly ash' as used herein refers to a solid powder having a chemical
30 composition similar to or the same as the composition of material that is produced during combustion of powdered coal, ie 25 to 60 wt% silica, 10 to 30 wt% Al_2O_3 , 5 to 25 wt% Fe_2O_3 , 0 to 20 wt% CaO and 0 to 5 wt% MgO.

- 5 -

Fly ash particles are typically spherical and range in diameter from 1 to 100 microns. In a preferred embodiment, the fly ash comprises two components. A first 'larger' size particles of fly ash with preferably a 100 micron maximum size. This size range of fly ash is used in the slurry to aid in improving the dewatering characteristics of the slurry but also as a moderately reactive pozzolan.

The second 'smaller' fly ash size zone which preferably has a 10 micron maximum size also adds an improving dewatering characteristic but is a more highly reactive pozzolan. This 'smaller' fly ash particle zone also improves the sanded surface quality of the finish layer.

In a preferred embodiment, the first fly ash comprises 10 to 60 wt% of the formulation based on total dry ingredients, more preferably 20 to 50 wt% and most preferably 30 to 40 wt%.

The second fly ash component preferably provides 5 to 30 wt% of the formulation based on total dry ingredients, more preferably 10 to 25 wt% and most preferably 15 to 20%.

In another preferred embodiment, the dewatering agent may include a coarse fraction fly ash which is greater than 100 microns. This coarse fraction fly ash includes bottom ash or similar products from coal combustion. There is an advantage to using these products over the aforementioned particle size fly ash since it is cheaper. Of course, as will be clear to persons skilled in the art, some reformulation of the slurry may be required to provide a suitable coating and appropriate dewatering characteristics when the dewatering agent is such a coarse fraction fly ash.

The coating may optionally contain other additives such as fillers. Such fillers may also be used to improve the dewatering characteristics of the slurry. For example, cenospheres (hollow ceramic microspheres) diatomite, wollastonite, ground rice hulls, ground perlite or the like, are particularly suitable for this purpose.

These and other fillers may also be used to provide additional benefits, for example calcium carbonates or alumina hydrates improve sandability and flexibility of the coated layer respectively. Silica flour improves hardness of the sanded surface of the coating layer and the acoustic/thermal insulation properties of the layer can be improved by including rubber particles, vermiculite, perlite, expanded polystyrene or gypsum.

- 6 -

The fillers preferably comprise 5 to 30 wt% of the formulation based on total dry ingredients, more preferably 10 to 25 wt% and most preferably 25 to 20 wt%.

The coating may also contain other organic additives. Cement plasticising agents, for example, may be used to alter the rheology of the slurry. Suitable cement
5 plasticising agents include melamine sulphonate formaldehyde condensates, naphthalene sulphonate formaldehyde condensates, naphthalene sulphonates, calcium lignosulphonates, sodium lignosulphonates, saccharose, sodium gluconate, sulphonic acids, carbohydrates, amino carboxylic acids, polyhydroxycarboxylic acids, sulphonated melomine and the like.

10 The amount of cement plasticiser of course will depend upon the fluidising ability of the particular plasticisers. Generally the quantity of plasticiser will be in the range of 0.3 to about 3 wt% and more preferably 0.5 to 2 wt% based on the total of dry ingredients in the formulation.

Particularly preferred cement plasticisers are Melment F-10, a melamine
15 formaldehyde sodium bisulphate polymer dispersant marketed by SKW-Trostburg in the form of a fine white powder. Another suitable plasticiser is Neosyn, a condensed sodium salt of sulphonated naphthalene formaldehyde available from Hodgson Chemicals.

Another preferred component in the coating is a biopolymer which acts to
20 enhance the flowability, segregation resistance and self levelling qualities of the cementitious slurry. Particularly suitable biopolymers are xanthan gum and/or whelan gum, eg KELCO-CRETE, K1C 376 manufactured by Monsanto.

Latex may also be included in the coating composition to improve adherence, elasticity, stability and impermeability of the coating. The latex also improves
25 flexibility of the formed coating.

The latex may be selected from the group consisting of acrylic latex, styrene latex, butadiene latex or mixtures thereof and is provided preferably in an amount between 0.5 to 20%, more preferably 1 to 15% and most preferably about 10% by weight of cement (on polymer solids basis) solids.

30 Vinyl polymers may also be incorporated into the coating either in addition or as a substitute to the latex emulsions. Such vinyl polymers or equivalent polymeric

- 7 -

materials enhance adhesion, resilience and flexural strength and abrasion resistance of the coating.

Preferred vinyl polymers include polyvinyl acetate or a copolymer vinyl acetate with another monomer such as ethylene. A particularly preferred vinyl acetate resin is
5 VINNAPAS LL5044 thermo plastic resin powder which contains a vinyl acetate-ethylene copolymer available from Wacker. Such powdered vinyl polymer is preferably provided in quantities similar to the latex emulsion referred to above.

In addition to the above, conventional other additives such as mineral oxides, hydroxides and clays, metal oxides and hydroxides, fire retardants such as magnesite,
10 thickeners, silica fume or amorphous silica, water sealing agents, water reducing agents, setting modifiers, hardeners, dispersants, foaming agents or flocculating agents, water-proofing agents and density modifiers are suitable for use with the present invention.

In this regard, one particular advantage arising from the present invention is the
15 ability to treat the product to be coated by providing additives in the coating. To explain, since the coating is dewatered through the product to be coated, it is possible to provide additives to the base layer by incorporation in the slurry. For instance, a waterproofing agent such as silane may be included in the coating in excess of the coating layers requirements. During dewatering, the silane will be drawn into and
20 through the base layer being coated thereby treating the base layer. This simultaneous treatment of the base layer as well as coating the base layer is a valuable additional benefit arising from the aforescribed method.

Best Mode for Carrying Out the Invention

The present invention will now be described by way of example only with
25 reference to the following embodiments.

In each of the following examples, the product was produces as follows.

Step 1 Slurry preparation

A slurry of the formulation is prepared by mixing the hydraulic binder, fly ash and other optional components with water. The solids content in the slurry is
30 preferably between 50 and 90%, more preferably 55 to 80% and most preferably 60 to 70%.

- 8 -

Step 2 Slurry application/dewatering

The slurry is applied to the base layer by any convenient means such as brushes rollers, knives or sprays etc. In a particular embodiment the slurry is applied by means of the apparatus and method subject of Australian Provisional Patent

- 5 Application Nos. PR3475 and PR3477, which are incorporated herein by reference.

The slurry is preferably designed to self level and form a uniform coating on the product. The building product to be coated exhibits a certain degree of porosity causing the slurry to dewater and form a uniform deposited cementitious layer. Time for dewatering can vary quite dramatically but normally occurs between 10 and

10 90 seconds, depending on the porosity of the material to be coated, its water content and thickness and viscosity of the slurry formulation. A vacuum may be used to reduce the slurry dewatering time if required. This is particularly useful when tailoring the coating process to the speed of a building product forming process, eg between 40 to 45 seconds on a Hatschek production line.

15 Step 3 Curing

After forming, the green laminate article comprising the building product plus coating is preferably precured for a short time, eg up to 48 hours, then cured by air/moist curing at room temperature, steam curing between 40 and 90°C or autoclaving in a steam pressure vessel between 120 and 200°C.

- 20 For either of these three curing techniques, a curing time range between 6 and 72 hours, preferably up to 48 hours, is suitable. Of course, as will be clear to persons skilled in the art, the length of time chosen for curing is dependent on the formulation, the manufacturing process and form of the article.

The following examples relate to specific formulation compositions.

25 Example 1: Sandable Dewatered Slurry Composition

Function: sandable, durable finishing layer for façade applications.

- The low viscosity slurry (drainage time in 50 ml volume funnel = 3.4 seconds) was applied on the base layer (Hardiform™ 12 mm thick cellulose fibre reinforced cement-based green sheet manufactured by James Hardie Industries). The slurry
- 30 dewatered in 90 seconds (un-aided by vacuum) forming a 1.25 mm thick coating. The coated sheet was autoclave-cured for 8 hrs at 180 °C temperature and 0.80 MPa

- 9 -

pressure. It was then sanded flat to 0.60 mm thick using industrial sanders equipped with 100 grit sand paper belts.

- 10 -

Slurry Composition	% by total weight of solids (S)	Weight in gm
Dewatered Cementitious Composition		
Portland Cement	30	12000
Silica Flour (400 G grade)	10	4000
Fly ash (larger size fraction)	40	16000
Fly ash (smaller size fraction)	20	8000
Total	100	40000
Water (W)		14000
Water/ Solids (W/S ratio)	0.35	
Solids Content (W/W+S)	0.74	
Organic Additives		
Welan Gum (Kelcocrete)	0.0075	3.0
naphthalene formaldehyde Plasticising Agent (Neosyn)	0.25	100.0
Acrylic Emulsion Rhoplex MC1934	1.0	400.0

Example 2: Rubberised Dewatered Slurry Composition

Function: Finishing layer in skid-resistant flooring, hard wearing static

- 5 dissipative flooring and acoustic insulating ceiling panels.

The low viscosity slurry (drainage time in 50 ml volume funnel = 4.2 seconds) was applied on the base layer (Hardiform™ 12 mm thick cellulose fibre reinforced cement-based green sheet manufactured by James Hardie Industries). The slurry dewatered in 60 seconds (un-aided by vacuum) forming a 1.25 mm thick coating. The coated sheet was autoclave-cured for 8 hrs at 180 °C temperature and 0.80 MPa pressure. It was then sanded flat to 0.60 mm thick using industrial sanders equipped with 100 grit sand paper belts.

- 11 -

Slurry Composition	% by total weight of solids (S)	Weight in gm
Dewatered Cementitious Composition		
Portland Cement	30	12000
Recycled Rubber crumbs (minus 30 mesh)	10	4000
Fly ash (larger size fraction)	40	16000
Fly ash (smaller size fraction)	20	8000
Total	100	40000
Water		13000
Water/ Solids (W/S ratio)	0.325	
Solids Content (W/W+S)	0.755	
Organic Additives		
Welan Gum (Kelcocrete)	0.0075	3.0
naphthalene formaldehyde Plasticising Agent (Neosyn)	0.25	100.0
Acrylic Emulsion Rhoplex MC1934	1.0	400.0

Example 3: Flexible & Sandable Dewatered Slurry Composition

- 5 **Function:** Flexible & sandable finishing layer on thin fibre cement reinforced cement-based lining.

The low viscosity slurry (drainage time in 50 ml volume funnel = 2.8 seconds) was applied on the base layer (Hardiflex™ 4.5 mm thick cellulose fibre reinforced cement-based green sheet manufactured by James Hardie Industries). The slurry dewatered in

10 120 seconds (un-aided by vacuum) forming a 1.25 mm thick coating. The coated sheet was precured for 48 hours then was autoclave-cured for 8 hrs at 180 °C temperature and 0.80 MPa pressure. It was then sanded flat to 0.60 mm thick using industrial sanders equipped with 100 grit sand paper belts.

- 12 -

Slurry Composition	% by total weight of solids (S)	Weight in gm
Dewatered Cementitious Composition		
Portland Cement	20	8000
Calcium Carbonate Grade 10 (40um avg. size)	10	4000
Alumina Tri-hydrate (80 um avg. size)	5	2000
Fly ash (larger size fraction)	45	18000
Fly ash (smaller size fraction)	20	8000
Total	100	40000
Water		12000
Water/ Solids (W/S ratio)	0.30	
Solids Content (W/W+S)	0.77	
Organic Additive		
Welan Gum (Kelcocrete)	0.0075	3.0
naphthalene formaldehyde Plasticising Agent (Neosyn)	0.25	100.0
Styrene Acrylic Latex Emulsion (56% solids)	5	2000

Example 4: Flexible & Sandable Dewatered Slurry Composition (Low Cement)

Function: Flexible & sandable finishing layer on thin fibre cement reinforced cement-based lining.

5

The low viscosity slurry (drainage time in 50 ml volume funnel = 4.5 seconds) was applied on the base layer (Hardiflex™ 4.5 mm thick cellulose fibre reinforced cement-based green sheet manufactured by James Hardie Industries). The slurry dewatered in 90 seconds (un-aided by vacuum) forming a 1.25 mm thick coating. The coated sheet was autoclave-cured for 8 hrs at 180 °C temperature and 0.80 MPa

10

- 13 -

pressure. It was then sanded flat to 0.60 mm thick using industrial sanders equipped with 100 grit sand paper belts.

Slurry Composition	% by total weight of solids (S)	Weight in gm
Dewatered Cementitious Composition		
Portland Cement	10	4000
Calcium Carbonate Grade 10 (40um avg. size)	20	8000
Alumina Tri-hydrate (80 um avg. size)	5	2000
Fly ash (larger size fraction)	40	18000
Fly ash (smaller size fraction)	25	10000
Total	100	40000
Water		16000
Water/ Solids (W/S ratio)	0.40	
Solids Content (W/W+S)	0.715	
Organic Additives		
Welan Gum (Kelcocrete)	0.0075	3.0
naphthalene formaldehyde Plasticising Agent (Neosyn)	0.25	100.0
Vinyl acetate-ethylene powdered copolymer (Vinnapas LL5004)	1.625	650

- 5 The aforementioned examples provide a coated product comparable in workability to monolithic or single layer composites. They can be flexed, cut, drilled or fixed by nails or the like to a frame without surface cracking or chipping.

The surface is 'finish-ready' and remains smooth, flat, crack-free and with low permeability even when used in a curved configuration.

- 10 Each examples provided excellent interlaminar bond between the base sheet and coating exhibiting good composite action, compatibility and resistance to delamination.

- 14 -

It can be seen that the present process provides a significant improvement not only in the attributes of the product but also in the ability to tailor the surface finish of a building product to match particular requirements. Examples of particular formulations to provide the desired finish characteristic include

- 5 a) Terrazzo (hardwearing decorative finish) - the finishing layer of the dewatered slurry can contain marble chips and pigmented cements and fillers. It may then be sanded and polished to form a hardwearing decorative finish. Such a coating on, for example, a fibre cement backing board, could be used as flooring tiles, decorative wall lining or external prefinished fibre cement cladding.
- 10 b) Stucco (orange peel) Finish -this may be achieved by manipulating speed and volume of the applied slurry to achieve a stucco look on the finishing layer. Once again, such a product may be used as an external pre-finished cement cladding.
- c) Sandable finish - this is probably the simplest and most straightforward application of the coating technique to provide a coating layer which may be sanded
15 and sealed, thereby providing a paint ready smooth, crack-free and low permeable surface. Such a product may be used for a variety of internal and external uses.
- d) Flexible finish - the coating layer may include various fillers and other additives to improve its flexibility, eg ethylene vinyl acetate, styrene butadiene rubber, styrene acrylic. It is designed to be a sandable, workable ie by score and snap,
20 nailable, crack-free, non-chipping, flexible and bendable, paint ready surface. Such a coating could normally be applied to reasonably thin building product to permit flexibility. It has a wide variety of uses but is particularly suitable as an internal lining in wet area applications or as an external cladding element, eg as a paint ready fibre cement siding.
- 25 e) Skim-coated finish - such a coating of the dewatered slurry may be applied to gypsum based building products thereby providing a smooth, flat, pre-skim coated and paint ready surface.
- f) Rubberised finish - by the addition of rubber crumbs into the slurry formulation, a coating layer may be provided on say a fibre cement backing for use as
30 a skid resistant flooring, hardwearing static dissipative flooring or acoustic insulating ceiling panels.

- 15 -

It will be understood by persons skilled in the art that the present invention may be embodied in other forms without departing from the spirit or scope of the inventive idea as described herein. In particular, it will be appreciated that the formulations, coatings, additives, methods and composite products of the present invention are
5 suitable or may be adapted for use in conjunction with the methods and apparatus as described in the various priority documents.

- 16 -

CLAIMS:

1. A method for coating a building product comprising providing a coating formulation including an hydraulic binder and a quantity of dewatering agent, producing a slurry of said formulation, applying said slurry to the product to be coated
5 and dewatering said slurry through said product.
2. A method according to claim 1, wherein the dewatering agent is provided in a sufficient quantity to maintain porosity in the slurry and the product to be coated during dewatering.
3. A method according to claim 1 or claim 2, wherein the dewatering agent is a
10 particulate material.
4. A method according to any one of the preceding claims, wherein the dewatering agent is selected from fly ash, alumina trihydrate, silica flour, cenospheres or mixtures thereof.
5. A method according to any one of the preceding claims, wherein the slurry has a
15 water content of up to 50%.
6. A method according to any one of the preceding claims, wherein, after coating, the coated product is cured by air curing, steam curing or hydrothermally cured in an autoclave.
7. A method according to any one of the preceding claims, wherein the product to
20 be coated is cementitious building board or product or gypsum building board.
8. A method according to any one of the preceding claims, wherein the coating includes fibres.
9. A method according to any one of the preceding claims, wherein the thickness of the coating layer on the product is between 0.1 and 10 mm.
- 25 10. A method according to any one of the preceding claims, wherein the thickness of the coating layer after sanding is between 0.05 and 5 mm.
11. A method according to any one of the preceding claims, wherein the hydraulic binder used in the coating is selected from the group consisting of white, grey or pigmented cements, hydraulic limes or mixtures thereof.
- 30 12. A method according to any one of the preceding claims, wherein the cements used in the coating are selected from the group consisting of Portland cement, blended

- 17 -

cements, blast furnace slag, pozzalans, masonry cement, oil well cement, natural cement, alumina cement, expansive cements or mixtures thereof.

13. A method according to any one of the preceding claims, wherein the binder in the formulation is between 10 and 50 wt% based on total dry ingredients.

5 14. A method according to any one of the preceding claims, wherein fly ash is the dewatering agent.

15. A method according claim 14, wherein the dewatering agent comprises:

i) 10 to 60% of the formulation based on total dry ingredients of a first fly ash component having a particle diameter between 1 and 100 microns; and

10 ii) 5 to 30 wt% of the formulation based on total dry ingredients of a second fly ash component having a maximum particle size diameter of around 10 microns.

16. A method according to any one of the preceding claims, wherein the dewatering agent includes a coarse fraction fly ash having a particle size diameter greater than 100 microns.

15 17. A method according to any one of the preceding claims, wherein the coating formulation includes additives to improve resultant properties of the coating.

18. A method according to any one of the preceding claims, wherein the formulation includes additives to improve workability and applicability of the slurry to the product to be coated.

20 19. A method according to any one of the preceding claims, wherein the formulation includes additives to improve the properties of the building product to be coated such that upon dewatering of the coating through the product, the building product is thus treated with said additive.

20. A method according to any one of the preceding claims, wherein dewatering
25 occurs with or without vacuum assistance

21. A formulation for use in coating a building product comprising an hydraulic binder and a quantity of dewatering agent sufficient to permit dewatering of a slurry produced from said formulation through the building product.

22. A formulation according to claim 21, wherein the dewatering agent is provided
30 in a sufficient quantity to maintain porosity in the slurry and the product to be coated during dewatering.

- 18 -

23. A formulation according to claim 21 or claim 22, wherein the dewatering agent is a particulate material.
24. A formulation according to any one of claims 21 to 23, wherein the dewatering agent is selected from fly ash, alumina trihydrate, silica flour, cenospheres or mixtures thereof.
25. A formulation according to any one of claims 21 to 24, wherein the coating includes fibres.
26. A formulation according to any one of claims 21 to 25, wherein the hydraulic binder used in the coating is selected from the group consisting of white, grey or pigmented cements, hydraulic limes or mixtures thereof.
27. A formulation according to any one of claims 21 to 26, wherein the cements used in the coating are selected from the group consisting of Portland cement, blended cements, blast furnace slag, pozzalans, masonry cement, oil well cement, natural cement, alumina cement, expansive cements or mixtures thereof.
28. A formulation according to any one of claims 21 to 27, wherein the binder in the formulation is between 10 and 50 wt% based on total dry ingredients.
29. A formulation according to any one of claims 21 to 28, wherein fly ash is the dewatering agent.
30. A formulation according to claim 29, wherein the dewatering agent comprises:
- i) 10 to 60% of the formulation based on total dry ingredients of a first fly ash component having a particle diameter between 1 and 100 microns; and
 - ii) 5 to 30 wt% of the formulation based on total dry ingredients of a second fly ash component having a maximum particle size diameter of around 10 microns.
31. A formulation according to any one of claims 21 to 30, wherein the dewatering agent includes a coarse fraction fly ash having a particle size diameter greater than 100 microns.
32. A formulation according to any one of claims 21 to 31, wherein the formulation includes additives to improve resultant properties of the coating.
33. A formulation according to any one of claims 21 to 32, wherein the formulation includes additives to improve workability and applicability of the slurry to the product to be coated.

- 19 -

34. A formulation according to any one of claims 21 to 33, wherein the formulation includes additives to improve the properties of the building product to be coated such that upon dewatering of the coating through the product, the building product is thus treated with said additive.
- 5 35. A dewaterable slurry for coating a building product, said slurry comprising water, an hydraulic binder and a quantity of dewatering agent sufficient to permit dewatering of said slurry through said building product.
36. A dewaterable slurry according to claim 35, wherein the dewatering agent is provided in a sufficient quantity to maintain porosity in the slurry and the product to
10 be coated during dewatering.
37. A dewaterable slurry according to claim 35 or claim 36, wherein the dewatering agent is a particulate material.
38. A dewaterable slurry according to any one of claims 35 to 37, wherein the dewatering agent is selected from fly ash, alumina trihydrate, silica flour, cenospheres
15 or mixtures thereof.
39. A dewaterable slurry according to any one of claims 35 to 38, wherein the slurry has a water content of up to 50%.
40. A dewaterable slurry according to any one of claims 35 to 39, wherein the coating includes fibres.
- 20 41. A dewaterable slurry according to any one of claims 35 to 40, wherein the hydraulic binder used in the coating is selected from the group consisting of white, grey or pigmented cements, hydraulic limes or mixtures thereof.
42. A dewaterable slurry according to any one of claims 35 to 41, wherein the cements used in the coating are selected from the group consisting of Portland cement, blended cements, blast furnace slag, pozzalans, masonry cement, oil well cement,
25 natural cement, alumina cement, expansive cements or mixtures thereof.
43. A dewaterable slurry according to any one of claims 35 to 42, wherein the binder in the formulation is between 10 and 50 wt% based on total dry ingredients.
44. A dewaterable slurry according to any one of claims 35 to 43, wherein fly ash is
30 the dewatering agent.
45. A dewaterable slurry according to claim 44, wherein the dewatering agent comprises:

- 20 -

- i) 10 to 60% of the formulation based on total dry ingredients of a first fly ash component having a particle diameter between 1 and 100 microns; and
- ii) 5 to 30 wt% of the formulation based on total dry ingredients of a second fly ash component having a maximum particle size diameter of around 10 microns.
- 5 46. A dewaterable slurry according to any one of claims 35 to 45, wherein the dewatering agent includes a coarse fraction fly ash having a particle size diameter greater than 100 microns.
47. A dewaterable slurry according to any one of claims 35 to 46, wherein the formulation includes additives to improve resultant properties of the coating.
- 10 48. A dewaterable slurry according to any one of claims 35 to 47, wherein the formulation includes additives to improve workability and applicability of the slurry to the product to be coated.
49. A dewaterable slurry according to any one of claims 35 to 48, wherein the formulation includes additives to improve the properties of the building product to be
- 15 coated such that upon dewatering of the coating through the product, the building product is thus treated with said additive.
50. A dewaterable slurry according to any one of claims 35 to 49, wherein the slurry is self levelling.
51. A dewaterable slurry according to any one of claims 35 to 50, wherein the
- 20 resultant dewatered slurry is curable by air curing, steam curing or hydrothermal curing in an autoclave.
52. A dewaterable slurry according to any one of claims 35 to 50, wherein the slurry may be applied to the product to be coated by splattering.
53. A composite product comprising a base structural layer with a coating thereon,
- 25 the coating including an hydraulic binder and a quantity of dewatering agent sufficient such that the coating may be dewatered through the base layer.
54. A composite product according to claim 53, wherein the dewatering agent is provided in a sufficient quantity to maintain porosity in the slurry and the product to be coated during dewatering.
- 30 55. A composite product according to claim 53 or claim 54, wherein the dewatering agent is a particulate material.

- 21 -

56. A composite product according to any one of claims 53 to 55, wherein the dewatering agent is selected from fly ash, alumina trihydrate, silica flour, cenospheres or mixtures thereof.
57. A composite product according to any one of claims 53 to 56, wherein the
5 coating and structure layer is cured by air curing, steam curing or hydrothermally cured in an autoclave.
58. A composite product according to any one of claims 53 to 57, wherein the product to be coated is cementitious building board or product or gypsum building board.
- 10 59. A composite product according to any one of claims 53 to 58, wherein the coating includes fibres.
60. A composite product according to any one of claims 53 to 59, wherein the thickness of the coating layer on the product is between 0.1 and 10 mm.
61. A composite product according to any one of claims 53 to 60, wherein the
15 thickness of the coating layer after sanding is between 0.05 and 5 mm.
62. A composite product according to any one of claims 53 to 61, wherein the hydraulic binder used in the coating is selected from the group consisting of white, grey or pigmented cements, hydraulic limes or mixtures thereof.
63. A composite product according to any one of claims 53 to 62, wherein the
20 cements used in the coating are selected from the group consisting of Portland cement, blended cements, blast furnace slag, pozzalans, masonry cement, oil well cement, natural cement, alumina cement, expansive cements or mixtures thereof.
64. A composite product according to any one of claims 53 to 63, wherein the binder in the formulation is between 10 and 50 wt% based on total dry ingredients.
- 25 65. A composite product according to any one of claims 53 to 64, wherein fly ash is the dewatering agent.
66. A composite product according to claim 65, wherein the dewatering agent comprises:
- i) 10 to 60% of the formulation based on total dry ingredients of a first fly ash
30 component having a particle diameter between 1 and 100 microns; and
 - ii) 5 to 30 wt% of the formulation based on total dry ingredients of a second fly ash component having a maximum particle size diameter of around 10 microns.

- 22 -

67. A composite product according to any one of claims 53 to 66, wherein the dewatering agent includes a coarse fraction fly ash having a particle size diameter greater than 100 microns.
68. A composite product according to any one of claims 53 to 67, wherein the
5 formulation includes additives to improve resultant properties of the coating.
69. A composite product according to any one of claims 53 to 68, wherein the formulation includes additives to improve workability and applicability of the slurry to the product to be coated.
70. A composite product according to any one of claims 53 to 69, wherein the
10 formulation includes additives to improve the properties of the building product to be coated such that upon dewatering of the coating through the product, the building product is thus treated with said additive.
71. A method of improving an hydraulic binder based coating formulation for coating a building product comprising adding to said binder a quantity of dewatering
15 agent such that after application of a slurry of said formulation to said building product, said slurry can be dewatered through the building product.
72. A method according to claim 71, wherein the dewatering agent is provided in a sufficient quantity to maintain porosity in the slurry and the product to be coated during dewatering.
- 20 73. A method according to claim 71 or claim 72, wherein the dewatering agent is a particulate material.
74. A method according to any one of claims 71 to 73, wherein the dewatering agent is selected from fly ash, alumina trihydrate, silica flour, cenospheres or mixtures thereof.
- 25 75. A method according to any one of claims 71 to 74, wherein the slurry has a water content of up to 50%.
76. A method according to any one of claims 71 to 75, wherein the coating includes fibres.
77. A method according to any one of claims 71 to 76, wherein the hydraulic binder
30 used in the coating is selected from the group consisting of white, grey or pigmented cements, hydraulic limes or mixtures thereof.

- 23 -

78. A method according to any one of claims 71 to 77, wherein the cements used in the coating are selected from the group consisting of Portland cement, blended cements, blast furnace slag, pozzalans, masonry cement, oil well cement, natural cement, alumina cement, expansive cements or mixtures thereof.
- 5 79. A method according to any one of claims 71 to 78, wherein the binder in the formulation is between 10 and 50 wt% based on total dry ingredients.
80. A method according to any one of claims 71 to 79, wherein fly ash is the dewatering agent.
81. A method according to claim 80, wherein the dewatering agent comprises:
- 10 i) 10 to 60% of the formulation based on total dry ingredients of a first fly ash component having a particle diameter between 1 and 100 microns; and
- ii) 5 to 30 wt% of the formulation based on total dry ingredients of a second fly ash component having a maximum particle size diameter of around 10 microns.
82. A method according to any one of claims 71 to 81, wherein the dewatering agent
- 15 includes a coarse fraction fly ash having a particle size diameter greater than 100 microns.
83. A method according to any one of claims 71 to 82, wherein the formulation includes additives to improve resultant properties of the coating.
84. A method according to any one of claims 71 to 83, wherein the formulation
- 20 includes additives to improve workability and applicability of the slurry to the product to be coated.
85. A method according to any one of claims 71 to 84, wherein the formulation includes additives to improve the properties of the building product to be coated such that upon dewatering of the coating through the product, the building product is thus
- 25 treated with said additive.
86. A dewatering aid for dewatering a cementitious slurry coating on a product, said dewatering aid comprising a quantity of particulate material sufficient to permit dewatering of the slurry through the product to be coated.
87. A dewatering aid according to claim 86, wherein the dewatering agent is
- 30 provided in a sufficient quantity to maintain porosity in the slurry and the product to be coated during dewatering.

- 24 -

88. A dewatering aid according to any one of claim 86 or claim 87, wherein the dewatering agent is selected from fly ash, alumina trihydrate, silica flour, cenospheres or mixtures thereof.
89. A dewatering aid according to any one of claims 86 to 88, wherein the product
5 through which the slurry is dewatered is a cementitious building board or product or gypsum building board.
90. A dewatering aid according to any one of claims 86 to 89, wherein the slurry includes fibres.
91. A dewatering aid according to any one of claims 86 to 90, wherein the coating
10 includes an hydraulic binder selected from the group consisting of white, grey or pigmented cements, hydraulic limes or mixtures thereof.
92. A dewatering aid according to any one of claims 86 to 91, wherein the coating includes cements selected from the group consisting of Portland cement, blended cements, blast furnace slag, pozzalans, masonry cement, oil well cement, natural
15 cement, alumina cement, expansive cements or mixtures thereof.
93. A dewatering aid according to any one of claims 86 to 92, wherein the coating includes a binder between 10 and 50 wt% based on total dry ingredients.
94. A dewatering aid according to any one of claims 86 to 93, wherein fly ash is the dewatering agent.
- 20 95. A dewatering aid according to claim 94, wherein the dewatering agent comprises:
i) 10 to 60% of the formulation based on total dry ingredients of a first fly ash component having a particle diameter between 1 and 100 microns; and
ii) 5 to 30 wt% of the formulation based on total dry ingredients of a second fly
25 ash component having a maximum particle size diameter of around 10 microns.
96. A dewatering aid according to any one of claims 86 to 95, wherein the dewatering agent includes a coarse fraction fly ash having a particle size diameter greater than 100 microns.
97. A dewatering aid according to any one of claims 86 to 96, wherein the
30 cementitious slurry coating includes additives to improve resultant properties of the coating.

- 25 -

98. A dewatering aid according to any one of claims 86 to 97, wherein the cementitious slurry coating includes additives to improve workability and applicability of the slurry to the product to be coated.

99. A dewatering aid according to any one of claims 86 to 98, wherein the
5 cementitious slurry coating includes additives to improve the properties of the product to be coated such that upon dewatering of the slurry through the product, the product is thus treated with said additive.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/AU02/00242

A. CLASSIFICATION OF SUBJECT MATTER																						
Int. Cl. ⁷ : B32B 13/00, E04C 1/40, 2/24, B28B 11/04																						
According to International Patent Classification (IPC) or to both national classification and IPC																						
B. FIELDS SEARCHED																						
Minimum documentation searched (classification system followed by classification symbols)																						
IPC: B32B 13/00, E04C 1/40, 2/24, B28B 11/04																						
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched																						
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)																						
DWPI: DEWATER+																						
C. DOCUMENTS CONSIDERED TO BE RELEVANT																						
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.																				
A	US 4840688 A (VOGT) 20 June 1989 whole document	1-99																				
A	US 5888322 A (HOLLAND) 30 March 1999 whole document	1-99																				
A	WO 99/08885 A (CLOWES) 25 February 1999 whole document	1-99																				
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C <input checked="" type="checkbox"/> See patent family annex																						
<p>* Special categories of cited documents:</p> <table border="0"> <tr> <td>"A"</td> <td>document defining the general state of the art which is not considered to be of particular relevance</td> <td>"T"</td> <td>later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>"E"</td> <td>earlier application or patent but published on or after the international filing date</td> <td>"X"</td> <td>document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>"L"</td> <td>document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>"Y"</td> <td>document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>"O"</td> <td>document referring to an oral disclosure, use, exhibition or other means</td> <td>"&"</td> <td>document member of the same patent family</td> </tr> <tr> <td>"P"</td> <td>document published prior to the international filing date but later than the priority date claimed</td> <td></td> <td></td> </tr> </table>			"A"	document defining the general state of the art which is not considered to be of particular relevance	"T"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	"E"	earlier application or patent but published on or after the international filing date	"X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	"L"	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y"	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	"O"	document referring to an oral disclosure, use, exhibition or other means	"&"	document member of the same patent family	"P"	document published prior to the international filing date but later than the priority date claimed		
"A"	document defining the general state of the art which is not considered to be of particular relevance	"T"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention																			
"E"	earlier application or patent but published on or after the international filing date	"X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone																			
"L"	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y"	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art																			
"O"	document referring to an oral disclosure, use, exhibition or other means	"&"	document member of the same patent family																			
"P"	document published prior to the international filing date but later than the priority date claimed																					
Date of the actual completion of the international search		Date of mailing of the international search report																				
23 April 2002																						
Name and mailing address of the ISA/AU		Authorized officer																				
AUSTRALIAN PATENT OFFICE PO BOX 200, WODEN ACT 2606, AUSTRALIA E-mail address: pct@ipaaustralia.gov.au Facsimile No. (02) 6285 3929		B. PREMARATNE Telephone No : (02) 6283 2407																				

INTERNATIONAL SEARCH REPORT

International application No.

PCT/AU02/00242

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	Derwent Abstract Accession No. 84-191733/31, Class P73, JP 59107985 A (NICHIASU KK) 22 June 1984 whole document	1-99
A	Derwent Abstract Accession No. 97-486254/45, Class L02, JP 09227200 A (NICHIIHA KK) 2 September 1997 whole document	1-99

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/AU02/00242

This Annex lists the known "A" publication level patent family members relating to the patent documents cited in the above-mentioned international search report. The Australian Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent Document Cited in Search Report		Patent Family Member					
US	4840688	EP	309709	DK	4955/88	FI	884165
		JP	1152008	NO	884036	CA	1307096
		DE	3730585				
US	5888322	NONE					
WO	9908885	AU	88151/98	GB	2328627		
							END OF ANNEX